Synthesis, Characterization and Optical Properties of PLA / P3HT Blends Thin Films

Maan Abd-Alameer Salih[1*], Q.S. Kareem[2], Mohammed Hadi Shinen[3]

Abstract

In this exploration Poly lactic corrosive (PLA) was orchestrated the ring-opening polymerization Poly lactic corrosive (PLA) blended with poly(3-hexylthiophene) (P3HT) which prepared by solution. Blends thin films Synthesis by spin coating technique and using Tetrahydrofuran (THF) as solvent. PLA powder was 'characterized by' 'X-ray' 'diffraction', '(FT-IR)'. pure Optical properties (PLA), (PLA)/P3HT blends thin films with different percentage of P3HT (0, 1, 2, and 3) wt% were investigated using UV-VS spectroscopy The results showed that the absorption, absorption coefficient, extinction coefficient and conductivity increase with increasing the rate of deformation P3HT, The energy gap decreases with increasing deformation.

Key Words: Poly Lactic Acid (PLA), Poly(3-hexylthiophene) (P3HT), Blends Thin Films and Optical Properties.

DOI Number: 10.14704/nq.2021.19.5.NQ21057 **NeuroQuantology 2021; 19(5):132-138**

Introduction

Polymers of novel piece have the properties of semiconductors, while essentially business polymers are cover. Realized that polymers are just molded, scientists and physicists happening middle the 20th sporadic twofold century to direct examinations intended to extend conductor polymers portrayed by the bonds, polymeric materials can be orchestrated and prepared into various shapes as indicated by the necessary application like slender movies [Chiang wt. al 1973]. Polymers partitioned into common and fake, the characteristic included proteins, starches, cellulose and elastic, either the modern. They have a great deal of properties and employments. The atoms in the polymer are a huge contrasted and particles hydrocarbon (where it is the establishment of the natural material), due to their size they are regularly alluded to as macromolecules [John 1992; Garlotta 2001; Yaarub et. al 2018]. Polymers have numerous attributes like ease, simple setup, high obstruction, adaptability, notwithstanding the mechanical properties of things, so it is utilized in electronic gadgets industry [Nampoothiri et. al 2010]. PLA intensifies dissolve well by dioxane or chloroform for the most part. In the solvents like toluene, CH3)2CO and THF, it liquefies in little amount at low temperature, yet softens well at bubbling temperature. Polymers dependent on lactic corrosive don't soften in methanol, ethanol, water, hexane and heptane [Yoo et. al 2006; Södergård et. al 2002]. Figure (1) below is the chemical Construction of Poly lactic corrosive (PLA) [Carrasco et. al 2010]. Figure (2) show Chemical Structure of P3HT.



Figure 1. Chemical Structure of Poly lactic acid (PLA).

Corresponding author: Maan Abd-Alameer Salih
Address: [1*]Physics Department, Colleges of Science, University of Babylon, Iraq; [2]Physics Department, College of Education, University of Al-Qadisiya, Iraq; [3]Physics Department, Colleges of Science, University of Babylon, Iraq.
[1*]E-mail: maan1974salih@yahoo.com
Relevant conflicts of interest/financial disclosures: The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.
Received: 17 March 2021 **Accepted:** 20 April 2021



Figure 2. Chmical Structure of P3HT

The Practical Aspect

Subject

This work is, Tetrahydrofuran (THF) solvent from Sigma-Aldrich, Pristine. P3HT was provided by Rieke Metals (4002-E; Lincoln, NE) with a sub-atomic weight (MW) of 51000g/mol and a dispersity of 2.4. PCBM was bought from Nano-C (Westwood, MA).

Poly-lactic Acid Production

PLA can be obtained utilizing a number guides 'As a rule, there are three strategies' which 'can be utilized to create excessive sub-atomic mass' PLA 'of round one hundred zero Daltons:' (a) 'immediate buildup polymerization;' (b) 'azeotropic dehydrative buildup and (c) 'polymerization thru lactide development, the ring-opening polymerization'. 'Right now, direct buildup and ring-opening polymerization are the most utilized advent processes. Ring-opening polymerization (ROP) of the lactide wishes catalyst however effects in PLA with' managed molecular weight. Depending on monomer used and controlling reactions conditions', it is feasible to manipulate the ratio and sequence of D- and L-lactic acid devices in the remaining polymer'. 'In this study, the ring-opening polymerization was once select'. The 'lactide' was once synthesized and PLA produced. [Auras et. al 2004].

Substrates Cleaning

The cleansing of substrates is very necessary system due to the fact the influences like oil or dirt have an effect on the residences of skinny movies, clean substrate is also essential to achieve good film adhesion.

Synthesis Thin Films

Pure PLA and PLA/P3HT skinny which are organized for this learn about are (45,44,42 and forty nm) for pure PLA and doped PLA through ratios (1%, 2% and 3%) of P3HT respectively, by means of the use of digital measuring device.

Analysis

X-ray Diffraction

Figure (3) suggests sample Poly lactic acid (PLA). It can be observed that it has amorphous nature with a diffraction top at 2θ =16.5° was observed, which corresponds to the attribute top of PLA and shows the development of a sure crystallinity diploma after processing [Zhang et. al 2011].



Fig. 3. X-Ray diffraction patterns of PLA.

(FT-IR)

Figure (4) represents FT-IR spectra of' synthesized pure PLA. 'The samples were' run 'in the' wave number (cm-1) 'range' between '4000 – 400' cm-1. The traits peaks of PLA inclusive of height at 1635.64 'cm–1, which 'is associated to the' amorphous carbonyl 'stretching' vibration 'of' PLA. 2,779.42cm-1 for uneven valence vibrations of CH3, 'Bands corresponding to bending vibrations of CH3 (asymmetric and symmetric' [**Nikolic et. al 2011**].



Fig. 4. FT-IR of Poly lactic acid (PLA)

Optical Properties

1. Absorption, Transmission PLA, PLA / P3HT Combo Thin

The UV in the area 300-900 nm at room temperature for PLA and PLA/ P3HT combo in fig. (5-A). The absorption spectrum of pure PLA has absorbance band at 389 nm, these bands had been assigned to π-π* digital transitions. The absorption PLA/ P3HT of (1%, 2% and three wt %) exhibit The shapes of UV – Vis spectra of composite are comparable to these of PLA. It was found that all the three absorption peaks figure. 5(a) for PLA/P3HT blends thin films are shifted to the right compare to those of PLA film or for high wavelength this, indicates the red shift which means energy gap film. In accordance with Beers law, The UV-VIS absorbance spectra agreement with reported in literature [Ali et. al 2017].

The transmittance spectra of PLA and PLA/P3HT films are shown in figure. (5-b). The transmittance spectra of PLA and PLA/P3HT movies are proven in figure. (5-b). The transmittance spectra for PLA confirmed almost 90% transmissions for wavelength larger than five hundred nm. [Gupta et. al 2007].





Fig. 5. '(a) Absorption, (b) Transmission, (c) Reflectance spectra as a functions of wave length for PLA, PLA/P3HT blend thin films.

2. The "Absorptions Coefficiente", Extinction Coefficient and Refractives Coefficient Spectra of Pure PLA and PLA / P3HT Blend Thin Films

PLA/P3HT blends. This similar to those observed by other worker [Oklobia 2016]. It can be actually considered that extinction coefficient, whereas the values of refractive index of PLA earlier than and after doping are proven in figures 6(c) The determine suggests that the refractive index values of pure polymer and its doping are growing linearly with these is settlement with [Khudair 2019; Rabee 2012].



Fig. 6. (a) Absorptions coefficient, (b) Extinctions coefficient, (c) refractive coefficient spectra a fun. of waves lengths for PLA, PLA /P3HT blend thin films

The Reale and Imaginary Dielectric Constants Spectra of Pure PLA and PLA / P3HT Blend Thin Films

Figures. 7(a and b), illustrates the variant of actual and imaginary components of dielectric' 'constant' respectively 'with wavelength for' of

pure PLA and PLA / P3HT mixture skinny films. It can be viewed that actual and imaginary components of dielectric consistent of P3HT, PLA/P3HT blends thin films. This similar to those observed by other worker [Auras et. al 2004].



Figure 7. (a) Reale dielectric constant, (b) Imaginary dielectric constant spectrae as a fune. of wave length PLA, PLA /P3HT blend thin films.

4. Optical Conductivity and Optical Band Gap of pure PLA and PLA / P3HT Blend Thin Films

$$\alpha h\nu = A\,(h\nu - E_g)^r \qquad (1)$$

The place hv is the strength of incident photon, Egis the optical strength band gap, A is a regular acknowledged as the disease parameter which is almost unbiased of photon strength parameter and m is the energy coefficient with the cost that is decided through the kind of viable digital transitions. For the direct and oblique allowed transition =1/2 or 2, respectively [**Abass et. al 2016**].

The fine line suit is got in the curve of r =1/2, which shows the kind of digital transition is direct allowed transition. The fee of optical band hole of Pure PLA and PLA / P3HT (1%.2% and 3%) can be established from figure9 (a, b, c and d) respectively w through extrapolating the linear element to $(\alpha h\omega)2 = 0$. Table (1) data the optical band hole of Pure PLA and PLA/P3HT blends skinny films. It was once discovered that the values of electricity hole reduce from 3.51 to 2.95 eV with growing of the weight share of P3HT, which skill a rising in conductivity [Fritzsche et. al. 1947].



Fig. 8. Shows the variation of optical conductivity with wavelength for PLA PLA/P3HT blend thin films.







Figure 9. Plots of $(\alpha h\nu)^2$ X. (hν): for (a) PLA , (b) PLA /P3HT (1%) , (c) PLA /P3HT (2%) and (d) PLA /P3HT (3%) blend thin films.

Table1. E_g(ev) values for pure PLA synthesized and PLA/P3HT blend thin films

Compound	E_g(ev)
Pure PLA	3.51
PLA/P3HT 1%	3.10
PLA/P3HT 2%	3.05
PLA/P3HT 3%	2.95

Conclusion

1. Optical properties have been measured in the range of (300-900) nm to prepare Pure PLA and PLA/P3HT (1%, 2%,and 3%%) blend thin films.
2. The electronic transition in pure polylactic acid(PLA) and PLA/P3HT blend thin films indicated direct allowed transition.
3. The energy gap of polylactic acid is 3.51ev and this value decreased within range of (3.51 – 2.95) eV when the concentration of P3HT increased.
4. The structure properties of Pure PLA and is confirmed by XRD and FT-IR characterizations.

References

Abass KH, Latif DM. The Urbach Energy and Dispersion Parameters dependence of Substrate Temperature of CdO Thin Films Prepared by Chemical Spray Pyrolysis. *International Journal of ChemTech Research* 2016; 9(9): 332-338.

Ali NA. Study the Optical Properties of Biodegradable Polylactic Acid / Silver Nanocomposites, worldwide journal of superior organic research. *International Journal of Advanced Biological Research* 2017; 7(2): 391-395.

Auras R, Harte B, Selke S. An overview of polylactides as packaging materials. *Macromolecular bioscience* 2004; 4(9): 835-864.

Carrasco F, Pagès P, Gámez-Pérez J, Santana OO, Maspoch ML. Processing of poly (lactic acid): Characterization of chemical structure, thermal stability and mechanical properties. *Polymer Degradation and stability* 2010; 95(2): 116-125.

Chiang CK, Druy MA, Gau SC, Heeger AJ, Louis EJ, MacDiarmid AG, Shirakawa H. Synthesis of highly conducting films of derivatives of polyacetylene, (CH) x. *Journal of the American Chemical Society* 1978; 100(3): 1013-1015.

Fritzsche H, Tauc J. *Amorphous and liquid semiconductors.* Plenum Press, New York 1974: 254.

Garlotta D. A literature review of poly (lactic acid). *Journal of Polymers and the Environment* 2001; 9(2): 63-84.

Gupta, B, Revagade, N, Hilborn, J. Poly (lactic acid) fiber: An overview. *Progress in polymer science*, 2007; 32(4): 455-482.

John R. *Electrochemical Studies of heterocyclic Conducting Polymers,* in Department of Chemistry. University of Wollongong 1992: 294.

Khudair MAS. *Proparation of Condicting Polymar (PANI:PEDOT) Blends and Study Their Optical and Electrical Properties for Solar mobile Application.* PhD thesis, University of Babylon 2019.

Nampoothiri KM, Nair NR, John RP. An overview of the recent developments in polylactide (PLA) research. *Bioresource technology* 2010; 101(22): 8493-8501.

Nikolic L, Ristic I, Adnadjevic B, Nikolic V, Jovanovic J, StankovicM. Novel microwave-assisted synthesis of poly (D, L-lactide): The influence of monomer/initiator molar ratio on the product properties. *Sensors* 2010; 10(5): 5063-5073.

Oklobia O. *Investigations of Thermally Induced Morphology in P3HT/PCBM Thin Films: Influence of Composition and Thermal Annealing on Photovoltaic Properties* (Doctoral dissertation, Staffordshire University) 2016.

Rabee BH. Study of Optical and Mechanical Properties for (PVAAgCO3) Composites. *European Journal of Scientific Research* 2012; 57(4): 191-209.

Södergård A, Stolt M. Properties of lactic acid based polymers and their correlation with composition. *Progress in polymer science* 2002; 27(6): 1123-1163.

Yoo DK, Kim D, Lee DS. Synthesis of lactide from oligomeric PLA: Effects of temperature, pressure, and catalyst. *Macromolecular research* 2006; 14(5): 510-516.

Zhang M, Thomas NL. Blending polylactic acid with polyhydroxybutyrate: The effect on thermal, mechanical, and biodegradation properties. *Advances in Polymer Technology* 2011; 30(2): 67-79.

Yaarub NA, Alshrefi SM, Rafea FAM, Ahmed T, Al-Mamoori, MHK, Al-Nafiey AK, Al-Kaim, AF. Optical and morphological characterizations of element Oxides Compound (Y2O3/SeO2) nano-composite structures synthesized via Chemistry of Laser Ablation. *Journal of Global Pharma Technology* 2018; 10(3): 536-544.

Zhang J. Application of diffusion weighted imaging with background body signal suppression in brain neurography. *NeuroQuantology* 2018; 16(3): 30-34.